



---

**Innovations Deserving  
Exploratory Analysis Programs**

**NCHRP IDEA Program**

## **Enhanced Performance Zinc Coating for Steel in Concrete**

---

Prepared by: Neal S. Berke, Ph.D. Tourney Consulting Group, LLC

**November 2016**

Final Report for NCHRP IDEA Project 174

---

 **TRANSPORTATION RESEARCH BOARD**

*The National Academies of*

**SCIENCES • ENGINEERING • MEDICINE**

### **Innovations Deserving Exploratory Analysis (IDEA) Programs Managed by the Transportation Research Board**

This IDEA project was funded by the NCHRP IDEA Program.

The TRB currently manages the following three IDEA programs:

The NCHRP IDEA Program, which focuses on advances in the design, construction, and maintenance of highway systems, is funded by American Association of State Highway and Transportation Officials (AASHTO) as part of the National Cooperative Highway Research Program (NCHRP).

The Safety IDEA Program currently focuses on innovative approaches for improving railroad safety or performance. The program is currently funded by the Federal Railroad Administration (FRA). The program was previously jointly funded by the Federal Motor Carrier Safety Administration (FMCSA) and the FRA.

The Transit IDEA Program, which supports development and testing of innovative concepts and methods for advancing transit practice, is funded by the Federal Transit Administration (FTA) as part of the Transit Cooperative Research Program (TCRP). Management of the three IDEA programs is coordinated to promote the development and testing of innovative concepts, methods, and technologies. For information on the IDEA programs, check the IDEA website ([www.trb.org/idea](http://www.trb.org/idea)). For questions, contact the IDEA programs office by telephone at (202) 334-3310. IDEA Programs Transportation Research Board 500 Fifth Street, NW Washington, DC 20001

The project that is the subject of this contractor-authored report was a part of the Innovations Deserving Exploratory Analysis (IDEA) Programs, which are managed by the Transportation Research Board (TRB) with the approval of the National Academies of Sciences, Engineering, and Medicine. The members of the oversight committee that monitored the project and reviewed the report were chosen for their special competencies and with regard for appropriate balance. The views expressed in this report are those of the contractor who conducted the investigation documented in this report and do not necessarily reflect those of the Transportation Research Board; the National Academies of Sciences, Engineering, and Medicine; or the sponsors of the IDEA Programs.

The Transportation Research Board; the National Academies of Sciences, Engineering, and Medicine; and the organizations that sponsor the IDEA Programs do not endorse products or manufacturers. Trade or manufacturers' names appear herein solely because they are considered essential to the object of the investigation.

## **Enhanced Performance Zinc Coating for Steel in Concrete IDEA Program Final Report Contract Number: NCHRP- 174**

### **1 IDEA PRODUCT 1.1 INTRODUCTION**

Current and future designs for bridges and other reinforced concrete structures exposed to deicing or marine chlorides requires improved corrosion resistance of the reinforcing steels in combination with higher quality concrete. Several stainless steel alloys are believed to have good performance, but the material costs are several times that of conventional black steel. In addition, though only the outer surface of the steel needs protection, the entire bar is made of alloys using premium raw materials.

A more sustainable approach considering initial material costs would be to use black steel with a protective coating, such as in hot-dipped galvanized (HDG) or epoxy-coated bars (ECR). If these bars provide enhanced corrosion protection, there can be a reduction in the overall life cycle cost versus black steel or stainless steel, using holistic approaches addressing the overall performance of the bar as a function of concrete properties and concrete cover over the bars, as performed in life-cycle modeling. These bars are subjected to mechanical damage in placement and in use due to cyclic loading of the concrete and the development of cracking. The potential for hydrogen embrittlement and coating application temperature limits the use of hot-dipped galvanized coating on some higher strength reinforcing bars that are desired for more efficient designs. Epoxy-coated reinforcement requires longer embedment lengths, and its lower bond might offset the use of higher strength steel bars.

## **1.2 PRODUCT**

The product that was the focus of investigation is a reinforcing bar with a thermal zinc diffusion (TZD) coating, with and without a supplemental organic coating. This TZD coating should have excellent bond to the steel as does the HDG coating, but is applied at lower temperatures than hot-dip galvanizing. This allows TZD coatings to be applied to higher strength steels without negative effects on the strength properties. It has a more porous surface than hot-dipped galvanized so that it should have a better bond to the concrete and is an excellent substrate for paint. The coating is significantly thinner using less zinc.


## **1.3 POTENTIAL IMPACT ON TRANSPORTATION PRACTICE**

TZD-coated reinforcement will have a significantly lower initial cost than stainless steel reinforcement, and can be applied to all strength grades of steel, allowing for potential additional savings where the designer can use higher tensile strengths to reduce the amount of reinforcing bars needed. When used with higher strength bars and lower permeability concrete, TZD could potentially lower the overall upfront and service life costs for bridges versus alternative reinforcing bar options.

## **2 CONCEPT AND INNOVATION**

A process of applying zinc to steel via thermal diffusion has been developed by Distek, NA, and has been in commercial use since 1993. The bars in this study were produced in the United States and coated in Michigan. The coating deposition temperatures (700–780°F) are lower than that in hot-dip galvanizing (840°F), but zinc-iron intermetallic phases form resulting in a metallurgical alloy bond between the zinc overlay and the steel substrate. The process results in a metallurgical conversion of the exterior surface into a porous zinc/iron alloy. The thermal diffusion process provides a very uniform coating that retains the original geometry of the part, as can be seen in Figure 1. It is hard and wear-resistant, and can withstand the rough handling and storage conditions generally expected in the field, as well as exhibiting ductility in bending and forming. Also, the thermal process is not susceptible to hydrogen embrittlement. Tests comparing the

performance in severe salt environments with and without abrasion show a 5 to 10 times improvement in performance with the TZD-coated steel versus HDG steel. Steel coated by this method is covered by ASTM A 1059 Standard Specification for Zinc Alloy Thermo-Diffusion Coatings (TDC) on Steel Fasteners, Hardware, and Other Products. Bars can be produced in lengths of 60 ft.



**FIGURE 1 Example of how TZD coating maintains the original geometry. Cross section of the nut shows that the internal threads are coated and maintain the thread geometry with a 25-micron coating (bright surface).**

Applying TZD to reinforcing bars is a recent application for this technology. The coating is not as thick as the zinc coating in HDG reinforcing bars, which helps to reduce cost and should help in workability. It has excellent abrasion resistance, based on current uses on chains used by the U.S. Navy, and the surface porosity should improve reinforcement bond to the concrete. The higher porosity should be beneficial for a two-component coating where the top coat would be an organic coating.

As noted earlier, the coating is very uniform even over ribs in the bars and is a low-temperature process. This could potentially be applied to higher strength reinforcement. This could potentially result in improved cracking behavior and a reduction in the cross-sectional requirements for the steel. The TZD coating applied to higher strength (grades 75 to 100) reinforcing bars could provide cost savings (less steel required), offsetting the initial upfront cost of the bars, where designs allow for reducing the required reinforcement for higher tensile strength reinforcement.

Summary:

The advantages to considering the use of TZD and TZE are:

- Equal to or lower cost than HDG at better performance
- Improved bond, potentially reducing crack width and migration of chlorides to bottom mat bars under surface cracks.
- Improved welding
- Low application temperatures which allow it to be applied to higher strength reinforcing bars to increase strength

## Prepared for the IDEA Program Transportation Research Board The National Academics

The review committee members are listed below:

Mario Paredes, Chairman—Florida DOT Ray

Bottenberg—Oregon DOT

Mike Brown—Virginia Transportation Research Center

Mike Dallaire—FHWA, Eastern Lands

Ted Hopwood—Kentucky Transportation Research Center

Steve Kahl—Michigan DOT

Daryl Little—U.S. Bureau of Reclamation