



ArmorGalv® PRODUCT DESIGNATION

The **ArmorGalv®** finish always starts with the **ArmorGalv®** TDG base coat per ASTM-A1059 A/M which is a thermally diffused Zinc/Iron alloy, that can be specified with a thickness from 15 to 120μ (.0006”-.005”)

The following chart is a description of basic standard **ArmorGalv®** Coatings offered. Not ALL are listed - please call or e-mail if additional information is required.

All **ArmorGalv®** Coatings are REACH, RoHS and Prop65 Compliant

A/G COATING	PROCESS/ COLOR	SALT SPRAY MIN.	TOPCOAT	SELF HEALING	PAINTABLE
A/G 1500	GRAY	1,500 HRS	SILFLEX®	NO	YES
A/G 2000	GRAY	2,000 HRS	TRITOP® 40	NO	YES
A/G 3000	GRAY	3,000 HRS	TRITOP® 40 + SILFLEX®	YES	YES
A/G Enhanced 5000	GRAY	5,000 HRS	TRITOP® 40 + SILFLEX®+ STRAUS UV WAX	YES	NO
A/G 2500 BLACK	BLACK	2,500 HRS	TRITOP 2 BLACKTOP W	NO	YES
ARMORPLEX PTFE COLORS	VARIOUS	> 5000 HOURS	TRITOP® 40 PTFE PAINT	N/A	YES

